

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 659 904 A2

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **95103705.0**

(51) Int. Cl.⁶: **C23C 16/40, C01B 33/00,
C08G 77/00**

(22) Date of filing: **12.05.92**

This application was filed on 15 - 03 - 1995 as a divisional application to the application mentioned under INID code 60.

(30) Priority: **28.05.91 US 706464**

(43) Date of publication of application:
28.06.95 Bulletin 95/26

(60) Publication number of the earlier application in accordance with Art.76 EPC: **0 516 308**

(84) Designated Contracting States:
BE DE ES FR GB IT NL

(71) Applicant: **DOW CORNING CORPORATION**
3901 S. Saginaw Road
Midland
Michigan 48686-0994 (US)

(72) Inventor: **Gentle, Theresa Eileen**
2319 Quail Run Drive
Midland,
Michigan (US)

(74) Representative: **Kyle, Diana**
Elkington and Fife
Prospect House
8 Pembroke Road
Sevenoaks, Kent TN13 1XR (GB)

(54) **Vaporized hydrogen silsesquioxane for depositing a coating.**

(57) The present invention relates to compositions suitable for depositing coatings containing silicon and oxygen on a substrate. The compositions contain vaporized hydrogen silsesquioxane in a carrier gas.

EP 0 659 904 A2

The present invention relates to vaporized hydrogen silsesquioxane which is used to deposit a coating containing silicon and oxygen. The coating is deposited by introducing the hydrogen silsesquioxane vapor into a deposition chamber containing the substrate to be coated and then inducing reaction of the vapor to form the coating.

Numerous silica vapor deposition methods are known in the art and many are currently used in industry. Typically, such deposition methods involve decomposing a silicon source in the presence of oxygen and the substrate to be coated. For example, chemical vapor deposition (CVD) is used to decompose various silanes (eg., SiH_4 , H_2SiCl_2 , etc.) in the presence of a source of oxygen (eg., air, oxygen, ozone, NO_2 , etc.) for the deposition of protective or dielectric coatings.

Hydrogen silsesquioxane resin is likewise known in the art. For instance, Collins et al. in U.S. Patent No. 3,615,272 describe such resins and their method of manufacture. Similarly, Haluska et al. in U.S. Patent No. 4,756,977 teach the use of hydrogen silsesquioxane resin to form ceramic coatings on substrates. These patents, however, only describe the use of the resin in solution.

U.S. Patent No. 5,063,267 assigned to the same assignee hereof, describes fractionating hydrogen silsesquioxane resin into narrow molecular weight fractions. The application describes the low molecular weight fractions thereof as volatile but does not describe a utility for such materials.

The present inventor has now unexpectedly discovered that gaseous, low molecular weight hydrogen silsesquioxane can be used in conventional vapor deposition techniques to form silicon and oxygen containing coatings.

The present invention provides a composition for depositing a coating containing silicon and oxygen on a substrate said composition comprising vaporized hydrogen silsesquioxane in a carrier gas.

The present invention is based on the discovery that volatile fractions of hydrogen silsesquioxane resin can be used to form coatings on various substrates. The coatings produced by the techniques described herein are valuable as protective and dielectric layers on substrates such as electronic devices.

The term hydrogen silsesquioxane resin or H-resin is used in this application to describe various hydridosilane resins of the formula $\text{HSi}(\text{OH})_x(\text{OR})_y\text{O}_{z/2}$, in which each R is independently an organic group or a substituted organic group which, when bonded to silicon through the oxygen atom, forms a hydrolyzable substituent, $x = 0-2$, $y = 0-2$, $z = 1-3$, $x + y + z = 3$. Though not represented by this structure, these resins may contain a small number of silicon atoms which have either 0 or 2 hydrogen atoms attached thereto due to various

factors involved in their formation or handling.

The above hydridosilane resins are generally produced by a process comprising the hydrolysis and condensation of silanes of the formula HSiX_3 , wherein X is a hydrolyzable group. These reactions may result in a fully condensed $(\text{HSiO}_{3/2})_n$ resin or the hydrolysis and/or condensation may be interrupted at an intermediate point such that partial hydrolyzates (containing Si-OR groups) and/or partial condensates (containing SiOH groups) are formed.

Various methods for the production of H-resin have been developed. For instance, Collins et al. in U.S. Patent No. 3,615,272 describe a process of forming nearly fully condensed H-resin (which may contain up to 100-300 ppm silanol) comprising hydrolyzing trichlorosilane in a benzenesulfonic acid hydrate hydrolysis medium and then washing the resultant resin with water or aqueous sulfuric acid. Similarly, Bank et al. in U.S. Patent No. 5,010,159 teach methods of forming such resins comprising hydrolyzing hydridosilanes in an aryl-sulfonic acid hydrate hydrolysis medium to form a resin which is then contacted with a neutralizing agent. A preferred embodiment of this latter process uses an acid to silane ratio of about 6/1.

Other resins, such as those described by Frye et al. in U.S. Patent No. 4,999,397, those produced by hydrolyzing an alkoxy or acyloxy silane in an acidic, alcoholic hydrolysis medium or any other equivalent hydridosilane, are also functional herein.

The above soluble hydridosilane resins are then fractionated to obtain the low molecular weight species which can be volatilized in the deposition process of this invention. Any conventional technique for fractionating the polymer can be used herein. Particularly preferred, however, is the use of a variety of fluids at, near or above their critical point. This process is described in U.S. Patent No. 5,063,267 assigned to the same assignee hereof. The process described therein comprises (1) contacting the H-resin with a fluid at, near or above its critical point for a time sufficient to dissolve a fraction of the polymer; (2) separating the fluid containing the fraction from the residual polymer; and (3) recovering the desired fraction.

Specifically, the application describes charging an extraction vessel with a sample of H-resin and then passing an extraction fluid through the vessel. The extraction fluid and its solubility characteristics are controlled so that only the desired molecular weight fractions of H-resin are dissolved. The solution with the desired fractions of H-resin is then removed from the vessel leaving those H-resin fractions not soluble in the fluid as well as any other insoluble materials such as gels or contaminants.

The desired H-resin fraction is then recovered from the solution by altering the solubility characteristics of the solvent and, thereby, precipitating out the desired fraction. These precipitates are then merely collected in a separation chamber by a process such as simple filtration.

The extraction fluid used in this process includes any compound which, when at, near or above its critical point, will dissolve the fraction of H-resin desired and not dissolve the remaining fractions. Additional consideration, however, is usually given to the critical temperature and pressure of the solvent compound so that unreasonable measures are not necessary to reach the appropriate point. Examples of specific compounds which are functional include, but are not limited to, carbon dioxide and most low molecular weight hydrocarbons such as ethane or propane.

By such methods, one can recover the desired fraction of H-resin. Other equivalent methods, however, which result in obtaining the fractions described herein are also contemplated. For instance, methods such as solution fractionation or sublimation may also function herein.

The preferred fraction of H-resin to be used in the process of this invention is one which can be volatilized under moderate temperature and/or vacuum conditions. Generally, such fractions are those in which at least about 75% of the species have a molecular weight less than about 2000. Preferred herein, however, are those fractions in which at least about 75% of the species have a molecular weight less than about 1200, with those fractions in which at least about 75% of the species have a molecular weight between about 400 and 1000 (T8-T16) being particularly preferred. Additionally, it is contemplated that broad molecular weight materials may be used herein as the source of H-resin vapor. Volatilization of such material, however, often leaves a residue comprising non-volatile species.

Once the desired fraction of H-resin is obtained, it is vaporized and introduced into a deposition chamber containing the substrate to be coated. Vaporization may be accomplished by heating the H-resin sample above its vaporization point, by the use of vacuum or by a combination of the above. Generally, vaporization may be accomplished at temperatures in the range of 50-300°C. under atmospheric pressure or at lower temperature (near room temperature) under vacuum.

The amount of H-resin vapor used in the process of this invention is that which is sufficient to deposit the desired coating. This can vary over a wide range depending on factors such as the desired coating thickness, the area to be coated, etc. In addition, the vapor may be used at nearly any concentration desired. A dilute vapor is used, in

which the H-resin vapor may be combined with nearly any compatible gas such as air, argon or helium.

The vaporized H-resin is then reacted to deposit the coating on the substrate. Reaction of gaseous species is well known in the art and any conventional chemical vapor deposition (CVD) technique can be used herein. For example, methods such as simple thermal vapor deposition, photothermal vapor deposition, plasma enhanced chemical vapor deposition (PECVD), electron cyclotron resonance (ECR), jet vapor deposition or any similar technique may be used. These processes involve the addition of energy (in the form of heat, plasma, etc.) to the vaporized species to cause the desired reaction.

In thermal vapor deposition, the coating is deposited by passing a stream of the vaporized H-resin over a heated substrate. When the H-resin vapor contacts the hot surface, it reacts and deposits the coating. Substrate temperatures in the range of about 100-1000°C. are sufficient to form these coatings in several minutes to several hours, depending on the thickness desired. It is to be noted that environments which facilitate the desired deposition are used in the deposition chamber. For instance, reactive environments such as air, oxygen, oxygen plasma, ammonia, amines, etc. or inert environments may all be used herein.

In PECVD, the vaporized H-resin is reacted by passing it through a plasma field. The reactive species thereby formed are then focused at the substrate and readily adhere. Generally, the advantage of this process over thermal CVD is that lower substrate temperature can be used. For instance, substrate temperatures of about 20 up to about 600°C. are functional.

The plasmas used in such processes comprise energy derived from a variety of sources such as electric discharges, electromagnetic fields in the radio-frequency or microwave range, lasers or particle beams. Generally preferred in most plasma deposition processes is the use of radio frequency (10 kHz -10² MHz) or microwave (0.1-10 GHz) energy at moderate power densities (0.1-5 watts/cm²). The specific frequency, power and pressure, however, are generally tailored to the equipment.

Although the mechanism for this deposition is not clearly understood, it is postulated that the addition of energy to the vaporized H-resin induces reaction with oxygen and causes some rearrangement of the molecules so that a silicon and oxygen containing coating is formed on the substrate. These coatings generally comprise primarily silica, but they may also contain silicon suboxides and residual Si-OC and/or Si-OH.

The composition of this invention can be used to deposit desirable coatings in a wide variety of thicknesses. For instance, coatings in the range of from about a monolayer to greater than about 2-3 microns are possible. These coating may also be covered by other coatings such as further SiO₂ coatings, SiO₂/modifying ceramic oxide layers, silicon containing coatings, silicon carbon containing coatings, silicon nitrogen containing coatings, silicon nitrogen carbon containing coatings, silicon oxygen nitrogen containing coatings and/or diamond like carbon coatings. Such coatings and their mechanism of deposition are known in the art. Many are taught in U.S. Patent No. 4,973,526.

The choice of substrates to be coated is limited only by the need for thermal and chemical stability at the temperature and in the environment of the deposition vessel. Thus, the substrate can be, for example, glass, metal, plastic, ceramic or the like. It is particularly preferred herein, however, to coat electronic devices to provide a protective or dielectric coating.

The following non-limiting example is provided to illustrate the invention to those skilled in the art.

Example 1

Hydrogen silsesquioxane resin made by the method of Bank et al., U.S. Patent 5,010,159, was fractionated using the process of Example 1 in U.S. Patent No. 5,063,267 and a fraction with a Mw Peak = 437, Mn = 361, Mw = 414, Mz = 459 and D = 1.14 was collected.

The H-resin fraction was placed at one end of a tube furnace and a silicon wafer placed at the other end. Two temperature zones were then established in the furnace - a zone of about 100-200°C. at the H-resin end and a zone of about 325-415°C. at the wafer end. A flow of air was established through the furnace from the end which held the H-resin to the end which held the wafer. By this process, any H-resin which was volatilized in the low temperature zone was carried to the high temperature zone where it reacted and was deposited on the heated silicon wafer. The air flow was maintained for about 10 minutes. After the air flow was stopped, the furnace was cooled and the wafer removed.

Examination of the wafer showed that a thin coating had been deposited. FTIR analysis of the coating showed the typical silica band at 1062 cm⁻¹.

Claims

1. A composition for depositing a coating on a substrate said composition comprising vaporized hydrogen silsesquioxane in a carrier gas.

2. The composition of claim 1, in which the carrier gas is selected from inert gas, air, oxygen, oxygen plasma, ammonia, and amines.

3. The composition of claim 1, in which greater than 75% of the hydrogen silsesquioxane has a molecular weight of less than 2000.

4. The composition of claim 3, in which greater than 75% of the hydrogen silsesquioxane has a molecular weight of less than 1200.

5. A composition comprising hydrogen silsesquioxane in which greater than 75% of the species have a molecular weight between 400 and 1000.

6. Use of a composition comprising vaporized hydrogen silsesquioxane in a carrier gas for depositing a coating on a substrate.

7. Use according to claim 6 of a composition as defined in any of claims 2 to 5.

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number: **0 659 904 A3**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **95103705.0**

(51) Int. Cl.⁶: **C23C 16/40, C01B 33/00,
C08G 77/00, C09D 4/00**

(22) Date of filing: **12.05.92**

(30) Priority: **28.05.91 US 706464**

(43) Date of publication of application:
28.06.95 Bulletin 95/26

(60) Publication number of the earlier application in
accordance with Art.76 EPC: **0 516 308**

(84) Designated Contracting States:
BE DE ES FR GB IT NL

(98) Date of deferred publication of the search report:
06.12.95 Bulletin 95/49

(71) Applicant: **DOW CORNING CORPORATION**
3901 S. Saginaw Road
Midland
Michigan 48686-0994 (US)

(72) Inventor: **Gentle, Theresa Eileen**
2319 Quail Run Drive
Midland,
Michigan (US)

(74) Representative: **Kyle, Diana**
Elkington and Fife
Prospect House
8 Pembroke Road
Sevenoaks, Kent TN13 1XR (GB)

(54) **Vaporized hydrogen silsesquioxane for depositing a coating.**

(57) The present invention relates to compositions suitable for depositing coatings containing silicon and oxygen on a substrate. The compositions contain vaporized hydrogen silsesquioxane in a carrier gas.

EP 0 659 904 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 95 10 3705

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.5)
10 D,X	US-A-3 615 272 (COLLINS WARDE T ET AL) 26 October 1971	5	C23C16/40
A	* example 2 *	1-4,6,7	C01B33/00
11 A	EP-A-0 270 369 (DOW CORNING) 8 June 1988	1-7	C08G77/00
	* claim 1 *		C09D4/00
			TECHNICAL FIELDS SEARCHED (Int.Cl.5)
			C09D
			C08G
			C23C
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
THE HAGUE		13 October 1995	EkhuIt, H
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone			
Y : particularly relevant if combined with another document of the same category			
A : technological background			
O : non-written disclosure			
P : intermediate document			
T : theory or principle underlying the invention			
E : earlier patent document, but published on, or after the filing date			
D : document cited in the application			
L : document cited for other reasons			
A : member of the same patent family, corresponding document			

EPO FORM 1500 01.92 (P04C01)